

LOCTITE® AA 3038™

Known as LOCTITE® 3038™
December 2013

PRODUCT DESCRIPTION

LOCTITE® AA 3038™ provides the following product characteristics:

Technology	Acrylic
Chemical Type	Acrylic
Appearance, Resin (Component A)	Clear yellow gel ^{LMS}
Appearance, Hardener (Component B)	Viscous straw colored liquid ^{LMS}
Components	Two component - requires mixing
Viscosity	Medium, thixotropic
Cure	Two part acrylic
Mix Ratio, by volume - Part A: Part B	1 : 10
Application	Bonding
Specific Benefit	Bonds low energy plastic without pre-treatment

LOCTITE® AA 3038™ is designed primarily to bond e-coated metals (ECS) to glass fibre filled polypropylenes (PPGF) but can also be used on other low energy substrates such as LDPE and HDPE. The product is designed to work without surface pre-treatment. The product contains 0.25 mm fillers for bondline thickness control. The thixotropic nature of LOCTITE® AA 3038™ reduces the migration of liquid product after application to the substrate.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A:

Specific Gravity @ 20 °C	1.2
Viscosity, Cone & Plate, mPa·s (cP):	
Temperature: 25 °C, Shear Rate: 20 s ⁻¹	1,500 to 15,000 ^{LMS}
Color, APHA	1 to 3 ^{LMS}
Flash Point - See SDS	

Part B:

Specific Gravity @ 25 °C	1.0
Viscosity, Cone & Plate, mPa·s (cP):	
Temperature: 25 °C, Shear Rate: 20 s ⁻¹	6,000 to 18,000 ^{LMS}
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE

This product cures when the components are dispensed through a static mixer at room temperature.

Fixture Time

Fixture time is defined as the time to develop a shear strength of 0.1 N/mm².


Fixture Time, mixed, minutes:	
PPGF to ECS	≤70

Open Time

Open Time, mixed, minutes	4
---------------------------	---


Cure Speed vs. Temperature

The graph below shows the shear strength developed with time on ECS to PPGF at different temperatures and tested according to ISO 4587.



Cure Speed vs. Bond Gap

The rate of cure will depend on the bondline gap. Thin bond lines result in higher cure speeds, increasing the bond gap will decrease the rate of cure.



TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 24 hours @ 22 °C

Physical Properties:

Coefficient of Thermal Expansion, K ⁻¹ :	
Below T _g	178×10 ⁻⁶
Above T _g	145×10 ⁻⁶
Glass Transition Temperature, °C	57
Coefficient of Thermal Conductivity, W/(m·K)	0.436
Shore Hardness, ISO 868, Durometer D	65

Cured for 168 hours @ 22 °C

Physical Properties:

Elongation, at break, ISO 527-2, %		37
Tensile Strength, at break, ISO 527-2	N/mm ²	12.98
	(psi)	(1,880)
Tensile Modulus, ISO 527-2	N/mm ²	704
	(psi)	(102,080)

TYPICAL PERFORMANCE OF CURED MATERIAL**Adhesive Properties**

Cured for 72 hours @ 22 °C

Lap Shear Strength, ISO 4587:

PPGF to ECS	N/mm ²	≥8 ^{LMS}
	(psi)	(≥1,160)
PPGF to Polycarbonate	N/mm ²	5.5
	(psi)	(800)
Aluminum	N/mm ²	7.9
	(psi)	(1,150)
PPGF	N/mm ²	9.8
	(psi)	(1,420)
Polyamide (Nylon)	N/mm ²	2.9
	(psi)	(420)
Polybutylene Terephthalate (PBT)	N/mm ²	13.6
	(psi)	(1,970)

Cured for 24 hours @ 22 °C

Lap Shear Strength, ISO 4587:

PPGF to ECS	N/mm ²	8.4
	(psi)	(1,220)

Cured for 168 hours @ 22 °C

Lap Shear Strength, ISO 4587:

PPGF to ECS	N/mm ²	10.5
	(psi)	(1,520)

TYPICAL ENVIRONMENTAL RESISTANCE


Cured for 24 hours @ 22 °C

Lap Shear Strength, ISO 4587:


PPGF to ECS

Hot Strength

Tested at temperature

**Heat Aging**

Aged at temperature indicated and tested @ 22 °C

**Chemical/Solvent Resistance**

Aged under conditions indicated and tested @ 22°C.

Environment	°C	% of initial strength		
		100 h	500 h	1000 h
98% RH	40	112	103	94
Motor oil	22	106	110	107
Motor oil	50	132	96	111
Water/glycol	22	114	102	99
Water/glycol	50	109	102	91

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for use:

- For best performance bond surfaces should be clean and free from grease.
- For more detailed information, please contact your local Technical Service Center or Customer Service Representative.

Loctite Material Specification^{LMS}

LMS dated September 18, 2006 (Part A) and LMS dated September 26, 2007 (Part B). Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Loctite Quality.

Storage

Store product in the unopened container in a dry location. Material removed from containers may be contaminated during use. Do not return liquid to original container. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those recommended. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology

Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.5