

Scotch-Brite[™] Light Grinding and Blending Discs

Product Data Sheet

Date 04_2019 Supersedes: -

Product Name	Light Grinding and Blending GB-DH, GB-DM, GB-DN, GB-DR, GB-DS
Product Description	3M Light Grinding and Blending products are non-woven abrasive with a scrim backing. The ceramic Cubitron™ mineral improves the cut and life performance. The Next Generation Technology used to coat Light Grinding and Blending allows the product to provide continuous cut as it wears through to the backing. Used for deburring, blending and finishing on metal.
Mineral	Blend of aluminum oxide mineral and Ceramic Grain
Fibre/ Bond/	Nylon Phenolic Resin
Grades	<i>Grade Front Color Back Color Print Color</i> Heavy Duty Maroon Maroon Black Super Duty Blue Maroon Black
Thickness/ Dimensions	6,35mm Hook-and-Loop Discs, Roloc Discs
Identification	All relevant product identification information can be found on the product label or on the box in which the product was received or on the with the product supplied Safety Instruction Leaflet.
Recommended (Ideal) Storage Conditions	Store under "first-in - first-out" base and at recommended conditions (16-26°C/ 35-50% rH). Temperature and humidity beside these conditions should be avoided.

Safety	Please refer to all local safety and industrial standards. Always use appropriate PPE and follow safety precautions as instructed in the associated Product Safety Insert. Product Safety Inserts are included with shipped product and are also available on-line through 3M.com <u>This product needs to be used with accessories 3M Roloc™ Disc Pads, Type</u> <u>TR, TS or TSM and 3M Disc Pad Holders (Hook-and-Loop) as indicated.</u> For information please contact your local 3M Office. <u>www.3M.com</u>
For Additional Information	To request additional product information or to arrange for sales assistance, call your local 3M Application Engineering
Important Notice	All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law
Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations	

3M is a trademark of the 3M Company

Г

3M Nederland B.V. Abrasives Systems Division Molengraaffsingel 29 2629 JD Delft NEDERLAND

www.3M.nl/abrasives