

## HYLOMAR JOINTING Compound

### Non-setting sealant and gasket compound for threaded and flanged joints

#### Product Overview

ROCOL® HYLOMAR JOINTING Compound is a blue non-setting sealant for the effective sealing of metal to metal & most plastic to plastic components.

ROCOL HYLOMAR JOINTING Compound can withstand high temperatures and vibration often found in demanding jointing applications.

ROCOL HYLOMAR JOINTING Compound is particularly effective for sealing flanges subjected to extreme vibration and distortion.

#### Typical Applications

ROCOL HYLOMAR JOINTING Compound is resistant to a wide range of fluids including all industrial fuels, oils, water, brine, air, turbine and piston engine combustion products, water, water/glycol, methanol mixtures, petroleum, synthetic diester lubricating oils, gasoline, lubricating oils, gasoline, kerosene fluids and most fluorocarbon refrigerants.

#### Features and Benefits

- ROCOL HYLOMAR JOINTING Compound has an excellent temperature range from -50°C to 250°C.
- ROCOL HYLOMAR JOINTING Compound can resist pressures of up to 35 bar (500 psi).
- Joints sealed with ROCOL HYLOMAR JOINTING Compound are easy to break and clean.
- ROCOL HYLOMAR JOINTING Compound is non-setting and non-hardening and resists vibration, thermal expansion and contraction of joints.

#### Directions for Storage and Use

- ROCOL HYLOMAR JOINTING Compound should not be applied in sub-zero temperatures.
- Ensure surfaces are clean and free of contaminants before applying ROCOL HYLOMAR JOINTING Compound.
- Apply a bead of ROCOL HYLOMAR JOINTING Compound from the tube which can then be spread out by hand or with a brush if required.
- Joints should be assembled within 15 minutes of applying the ROCOL HYLOMAR JOINTING Compound.
- Pressure testing should only be carried out after the ROCOL HYLOMAR JOINTING Compound has been allowed to dry for a minimum of 30 minutes at an ambient temperature of 20°C to 25°C. Drying time will be lengthened if the ambient temperature is lower.
- The storage temperature of ROCOL HYLOMAR JOINTING Compound should be controlled between +1°C and +40°C.
- The shelf life of ROCOL HYLOMAR JOINTING Compound is 1 years from date of manufacture.

#### Pack Sizes

Pack Size	Part Code
100g	28060

## HYLOMAR JOINTING Compound

Non-setting sealant and gasket compound for threaded and flanged joints

Property	Test Method	Result
Appearance	Visual	Soft blue paste
Base Type	N/A	Polyester urethane & solvent
Solids	N/A	Silica
Temperature Range	N/A	-50°C to 250°C
Pressure Resistance	N/A	35 bar (500 psi)
Thickness of Residue	N/A	0.03mm
Surface Finish	N/A	3.0 micron maximum
Area covered by 100g	N/A	1.275m <sup>2</sup>

Values quoted above are typical and do not constitute a specification.

### Safety Data Sheets

Safety data sheets are available for download from our website [www.rocol.com](http://www.rocol.com) or may be obtained from your usual ROCOL contact.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

Issue: 2 Date: 03-11

T +44 (0) 113 232 2600  
F +44 (0) 113 232 2740  
E [customer-service@rocol.com](mailto:customer-service@rocol.com)  
[www.rocol.com](http://www.rocol.com)

ROCOL House, Swillington, Leeds LS26 8BS

Registered Company No. 559693 VAT No. 742 0531 67  
Registered Office: Admiral House, St Leonard's Road, Windsor, Berkshire SL4 3BL

ROCOL A division of *ITW* Ltd



BS EN ISO 9001  
Certificate No. FM 12448



BS EN ISO 14001  
Certificate No. EMS 67596



OHSAS 18001  
Certificate No. OHS 78173



INVESTORS  
IN PEOPLE